



ESPECIFICACIONES DE BOBINAS GALVANIZADAS Y PRE-PINTADAS PARA GRUPO LUVITEC

CARACTERISTICAS	ESPECIFICACIONES
Type of Base Steel	SAE 1006
Base Substrate:	As per ASTM A 653, CSB, Z 180 gsm Skin passed Levelled. Tolerance 50% according to ASTM A 924
Top Coat	20 Microns RMP RAL 9010 paint + 5 Microns Primer. As per ASTM A755
Back Coat	8-10 mic R CSB, Z-180 gsm (min). As per ASTM A 755
Gloss:	As per approved sample
Coil ID	508 mm
Coil weight:	2 Ton max
Packing:	Export Sea Worthy
Guard Film:	No
Loading:	Eye to side without wooden skids.
End Use:	Stading Seam roofong
Tensile strength	1.400 Kg/cm2.
Strip Width	605 mm.
Thickness	0.5 mm. 0.6 mm. 0.7 mm. 0.9 mm.